

Accepted Manuscript

Electrically conductive polymer nanofiber composite with an ultralow percolation threshold for chemical vapour sensing

Jiefeng Gao, Hao Wang, Xuewu Huang, Mingjun Hu, Huaiguo Xue, Robert K.Y. Li



PII: S0266-3538(18)30374-9

DOI: [10.1016/j.compscitech.2018.04.014](https://doi.org/10.1016/j.compscitech.2018.04.014)

Reference: CSTE 7176

To appear in: *Composites Science and Technology*

Received Date: 13 February 2018

Revised Date: 5 April 2018

Accepted Date: 10 April 2018

Please cite this article as: Gao J, Wang H, Huang X, Hu M, Xue H, Li RKY, Electrically conductive polymer nanofiber composite with an ultralow percolation threshold for chemical vapour sensing, *Composites Science and Technology* (2018), doi: 10.1016/j.compscitech.2018.04.014.

This is a PDF file of an unedited manuscript that has been accepted for publication. As a service to our customers we are providing this early version of the manuscript. The manuscript will undergo copyediting, typesetting, and review of the resulting proof before it is published in its final form. Please note that during the production process errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

Electrically conductive polymer nanofiber composite with an ultralow percolation threshold for chemical vapour sensing

Jiefeng Gao,*¹ Hao Wang,¹ Xuewu Huang,¹ Mingjun Hu², Huaiguo Xue¹, Robert. K. Y. Li³

¹ School of Chemistry and Chemical Engineering, Yangzhou University, Yangzhou, Jiangsu, 225002, China

² School of Materials Science and Engineering, Beihang University, Beijing, China.

³ Department of Physics and Materials Science, City University of Hong Kong, Tat Chee Avenue, Kowloon, Hong Kong

Abstract

A flexible conductive polymer nanofiber composite (FCPNC) was prepared by carbon nanotube (CNT) decoration onto the blend polyurethane (PU)/Polyethersulfone (PES) nanofibers under the assistance of ultrasonication. CNTs were uniformly distributed on the nanofiber surface, which was beneficial to the construction of electrically conductive network. The obtained composite mat possessed an ultralow percolation threshold of 0.056 vol%, and the electrical conductivity was as high as 2.8 S m^{-1} at a relatively low CNT concentration of 0.85 vol%. Also, the introduction of CNTs increased both the tensile strength and Young's modulus of the nanofiber mat. The FCPNC with good electrical conductivity and interconnected porous structures was then used as a chemical vapour sensor, which was based on the change of the distance among the conductive nanofibers and hence the electrical conductivity, resulting from the adsorption and desorption of organic vapours. The sensing selectivity of the FCPNC was determined by the solubility parameters as well as the saturated vapour pressure. When the FCPNC with a CNT content of 0.5 vol% was exposed to the acetone vapour, the response intensity (R_I) could reach $\sim 8.8 \times 10^2$, while the response rate (R_R) was only 9 s. The resistance was able to return to its original value when the sample was taken out from the vapour to air, and the R_I could retain 90% after tenth cycle test, displaying a good reproducibility.

Keywords: Polymer-matrix composites (PMCs); Electrical properties; Scanning electron microscopy (SEM); Electro-spinning.

متن کامل مقاله

دریافت فوری ←

ISIArticles

مرجع مقالات تخصصی ایران

- ✓ امکان دانلود نسخه تمام متن مقالات انگلیسی
- ✓ امکان دانلود نسخه ترجمه شده مقالات
- ✓ پذیرش سفارش ترجمه تخصصی
- ✓ امکان جستجو در آرشیو جامعی از صدها موضوع و هزاران مقاله
- ✓ امکان دانلود رایگان ۲ صفحه اول هر مقاله
- ✓ امکان پرداخت اینترنتی با کلیه کارت های عضو شتاب
- ✓ دانلود فوری مقاله پس از پرداخت آنلاین
- ✓ پشتیبانی کامل خرید با بهره مندی از سیستم هوشمند رهگیری سفارشات